



Somos[®] Element

Stereolithography



A stereolithography material engineered to create flawless investment castings patterns.

Through continuous interaction with our customers, pattern makers and foundries, our team developed **Somos® Element** for producing investment casting patterns.

Somos® Element is an antimony-free stereolithography material that has been specifically designed to improve the repeatability and quality of 3D printed casting patterns. Patterns created with **Somos® Element** leave trace amounts of lightweight, easily-removable ash residue after burnout and have better green strength, so there's no worry of breakage during handling, while being dimensionally stable during storage. Any residue that is left behind is easily removed, leaving a perfectly clean void in the ceramic mold. This translates into lower mold prep times and lower rates of rework, saving customers time and money.

Key Benefits

- Trace amounts of ash that are lightweight and easily removed
- Suitable for high-end alloy castings
- Rapid draining
- Produces accurate, repeatable parts regardless of size

Technical Data

Liquid Properties		Optical Properties		
Appearance	Clear	E _c	10 mJ/cm ²	[critical exposure]
Viscosity	~125 cps @ 30°C	D _p	5.2 mils	[slope of cure-depth vs. ln (E) curve]
Density	1.11 g/cm ³ @ 25°C	E ₁₀	68.4 mJ/cm ²	[exposure that gives 0.254 mm (.010 inch) thickness]

Mechanical Properties		UV Postcure	
ASTM Method	Property Description	Metric	Imperial
D638-14	Tensile Modulus	3,170 MPa	460 ksi
D638-14	Tensile Strength at Break	53 MPa	7.7 ksi
D638-14	Elongation at Break	2.3%	
D570-98	Water Absorption	0.36%	
D790-15e2	Flexural Strength	114 MPa	16.6 ksi
D790-15e2	Flexural Modulus	3,230 MPa	468 ksi
D256-10e1	Izod Impact (Notched)	22 J/m	0.41 ft-lb/in
D2240-05	Durometer Hardness	86	

Thermal/Electrical Properties		UV Postcure	
ASTM Method	Property Description	Metric	Imperial
E831-13	C.T.E. -40–0°C (-40–32°F)	56.8 µm/m°C	31.5 µin/in°F
E831-13	C.T.E. 0–50°C (32–122°F)	75.7 µm/m°C	42.1 µin/in°F
E831-13	C.T.E. 50–100°C (122–212°F)	137 µm/m°C	76.1 µin/in°F
E831-13	C.T.E. 100–150°C (212–302°F)	142 µm/m°C	78.9 µin/in°F
D150-11	Dielectric Constant 60 Hz	3.7	
D150-11	Dielectric Constant 1 KHz	3.6	
D150-11	Dielectric Constant 1 MHz	3.4	
D149-09	Dielectric Strength	18.3 kV/mm	465 V/mil
E1545-11	Tg	58°C	136°F
D648-16	HDT @ 0.46 MPa (66 psi)	58°C	136°F
D648-16	HDT @ 1.81 MPa (264 psi)	53°C	127°F

Burnout Properties		
Method	Property Description	
ICP	Antimony Content	Not detectable (<3 ppm)
TGA	Ash Content	<0.005%

These values may vary and depend on individual machine processing and post-curing practices.

[More information at am.covestro.com](https://www.am.covestro.com)



Covestro Deutschland AG
Kaiser-Wilhelm-Allee 60
51373 Leverkusen
Germany

www.covestro.com

The manner in which you use our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, is beyond our control. Therefore, it is imperative that you test our products to determine suitability for your processing and intended uses. Your analysis must at least include testing to determine suitability from a technical, health, safety, and environmental and regulatory standpoint. Such testing has not necessarily been done by Covestro, and Covestro has not obtained any approvals or licenses for a particular use or application of the product, unless explicitly stated otherwise. If the intended use of the product is for the manufacture of a pharmaceutical/medicinal product, medical device¹ or of pre-cursor products for medical devices or for other specifically regulated applications which lead or may lead to a regulatory obligation of Covestro, Covestro must explicitly agree to such application before the sale. Any samples provided by Covestro are for testing purposes only and not for commercial use. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information, including technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed by you that you assume and hereby expressly release and indemnify us and hold us harmless from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent. These values are typical values only. Unless explicitly agreed in written form, they do not constitute a binding material specification or warranted values.

¹Please see the "Guidance on Use of Covestro Products in a Medical Application" document.
Edition: September 2021 · Printed in Germany