



Somos[®] WaterShed XC 1122

Stereolithography



Somos® WaterShed XC 1122

An easy to use, low viscosity, water-resistant stereolithography material for use in numerous applications.

As one of the industry's most popular materials, **Somos® WaterShed XC 1122** is the clear solution for numerous applications. Whether you're a designer looking for highly detailed parts with superior clarity and water resistance, or an engineer focusing on durability for functional testing, **Somos® WaterShed XC 1122** mimicks the look and feel of clear thermoplastics, such as ABS and PBT.

Somos® WaterShed XC 1122 produces optically clear parts with a smooth finish and it's ease of use helps to shorten product development and testing. This versatility means **Somos® WaterShed XC 1122** is the ideal material in markets such as automotive, aerospace and consumer electronics for applications including packaging, RTV patterns, durable concept models, wind tunnel testing and investment casting patterns.

Key Benefits

- Easy to use and finish
- Superior moisture resistance
- Exceptional clarity

Ideal Applications

- Consumer products
- Fluid/air flow analysis
- Duct work
- Investment casting
- Lenses

Technical Data

Liquid Properties		Optical Properties		
Appearance	Optically clear, near colorless	E _c	11.5 mJ/cm ²	[critical exposure]
Viscosity	~260 cps @ 30°C	D _p	6.5 mil	[slope of cue-depth vs ln (E) curve]
Density	~1.12 g/cm ³ @ 25°C	E ₁₀	54 mJ/cm ²	[exposure that gives 0.254 mm (.010 inch) thickness]
		D542	1.514	Index of Refraction (cured)

Mechanical Properties		UV Postcure	
ASTM Method	Property Description	Metric	Imperial
D638M	Tensile Strength at Break	50.4 MPa	7.3 ksi
D638M	Elongation at Break	15.5%	
D638M	Elongation at Yield	3%	
D638M	Tensile Modulus	2,770 MPa	402 ksi
D790M	Flexural Strength	68.7 MPa	10 ksi
D2240	Flexural Modulus	2,205 MPa	320 ksi
D256A	Izod Impact (Notched)	25 J/m	0.47 ft-lb/in
D570-98	Water Absorption	0.35%	

Thermal/Electrical Properties		UV Postcure	
ASTM Method	Property Description	Metric	Imperial
E831-05	C.T.E. -40–0°C (-40–32°F)	67 µm/m°C	37 µin/in°F
E831-05	C.T.E. 0–50°C (32–122°F)	93 µm/m°C	52 µin/in°F
E831-05	C.T.E. 50–100°C (122–212°F)	180 µm/m°C	100 µin/in°F
E831-05	C.T.E. 100–150°C (212–302°F)	187 µm/m°C	104 µin/in°F
D150-98	Dielectric Constant 60 Hz		4
D150-98	Dielectric Constant 1 KHz		3.8
D150-98	Dielectric Constant 1 MHz		3.5
D149-97a	Dielectric Strength	15.9 kV/mm	404 V/mil
E1545-00	T _g	43°C	109°F
D648	HDT @ 0.46 MPa (66 psi)	50°C	122°F
D648	HDT @ 1.81 MPa (264 psi)	49°C	120°F

These values may vary and depend on individual machine processing and post-curing practices.

[More information at am.covestro.com](http://am.covestro.com)



Covestro Deutschland AG
Kaiser-Wilhelm-Allee 60
51373 Leverkusen
Germany

www.covestro.com

The manner in which you use our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, is beyond our control. Therefore, it is imperative that you test our products to determine suitability for your processing and intended uses. Your analysis must at least include testing to determine suitability from a technical, health, safety, and environmental and regulatory standpoint. Such testing has not necessarily been done by Covestro, and Covestro has not obtained any approvals or licenses for a particular use or application of the product, unless explicitly stated otherwise. If the intended use of the product is for the manufacture of a pharmaceutical/medicinal product, medical device¹ or of pre-cursor products for medical devices or for other specifically regulated applications which lead or may lead to a regulatory obligation of Covestro, Covestro must explicitly agree to such application before the sale. Any samples provided by Covestro are for testing purposes only and not for commercial use. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information, including technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed by you that you assume and hereby expressly release and indemnify us and hold us harmless from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent. For more information on Covestro products in Medical Applications, please request from your sales support contact our Guidance document: GUIDANCE ON USE OF COVESTRO PRODUCTS IN A MEDICAL APPLICATION. These values are typical values only. Unless explicitly agreed in written form, they do not constitute a binding material specification or warranted values. The biocompatibility testing referenced above cannot assure the biocompatibility of final or intermediate products made from Covestro products or the suitability of such products for their use in a medical application, i.e., the test data cannot be used to conclude that any medical devices manufactured from the Covestro products meet the necessary requirements of ISO Standard 10993-1. It is the sole responsibility of the manufacturer of the final end-use product to conduct all necessary tests (including biocompatibility tests) and inspections and to evaluate the final product under actual end-use requirements.

¹Please see the "Guidance on Use of Covestro Products in a Medical Application" document.
Edition: September 2021 · Printed in Germany